

PAPER GRADES**TOTAL BALANCED T.E.A (j/m²)**

Extensible Brown Sack Kraft	Number of plies		
	1	2	3
EK 6 100gm	295	584	864
EK 6 90gm	256	507	750
EK 6 80gm	221	437	647
EK 6 75gm	216	428	633
EK 6 70gm	200	396	586

SEMI-EXTENSIBLE		
Brown	70gm	158
Brown	75gm	168
IMPORTED EXTENSIBLE		
Brown	70gm	209

The values above are given as an indication of typical values and may vary. Balanced T.E.A is relative to standard sack dimensions and becomes more important as the sack CD narrows

BALANCED T.E.A IS TYPICALLY CALCULATED AS : 1.5 CD t.e.a + MD t.e.a